



<b>QUALITY :</b>	<b>367- BERGEN</b>
------------------	--------------------

FABRIC DESCRIPTION	METHOD	
COMPOSITION % COTTON		100
USABLE WIDTH (cms)	BS EN 1773	147
NOMINAL LENGTH (mts)		100
WEAVE		3x1
WEIGHT g/sm	BS EN 12127	255

PHYSICAL PROPERTIES	METHOD	WARP	WEFT
TENSILE STRENGTH NEWTONS (MIN)	BS EN ISO 13934	900	550
TEAR STRENGTH NEWTONS (MIN)	BS EN ISO 13937-3	25	25
% SHRINKAGE TO WASHING (MAX) 50C	BS EN ISO 26330	3	3
% SHRINKAGE TO HEAT (MAX)		N/A	N/A

ABRASION RESISTANCE RUBS	BS EN ISO 12947	18000
PILLING RESISTANCE 10 HOURS	BS EN ISO 12945-1	4

COLOUR FASTNESS	METHOD	CHANGE	STAIN(PE)	STAIN(CTN)
WASHING	BS EN ISO 105 C06 E2	4		4
ACID PERSPIRATION	BS EN ISO 105 E04	4		4
ALKALI PERSPIRATION	BS EN ISO 105 E04	4		4
RUB FASTNESS (WET)	BS EN ISO 105 X12			
RUB FASTNESS (WET)	BS EN ISO 105 X12			2
RUB FASTNESS (DRY)	BS EN ISO 105 X12			3-4
LIGHT FASTNESS	BS EN ISO 105 B02	4		

THE ABOVE FIGURES ARE GUIDELINES ONLY AND SLIGHT VARIATIONS WITHIN COMMERCIAL TOLERANCES MAY OCCUR FROM TIME TO TIME.

THE SHRINKAGE WASHES ARE FOR ONE WASH ONLY, FURTHER WASHES WILL RESULT IN PROGRESSIVE SHRINKAGE PARTICULARLY ON COTTONS & CARE SHOULD BE TAKEN IN SIZING GARMENTS.

PLEASE CONSULT YOUR SUPPLIER IF IN ANY DOUBT.

ISSUE: 06.11.09