

EVERFLEX SILICONE 225 INDUSTRIAL AND GLAZING SILICONE

Colour	Product Code	Pack Size	Box Qty
White	225WE	C3	25
	FP225WE6	600ml	12
Translucent	225TR	C3	25
Black	225BK	C3	25
Brushed Steel	225STEEL	C3	25

Product Description

EVERFLEX SILICONE 225 is an acetoxy cure silicone sealant that cures quickly to provide a permanently flexible, high strength waterproof seal. Specifically designed for most glazing and industrial applications.

Benefits

- Permanently flexible.
- Quick curing - low dirt pick up.
- Temperature resistant to 200°C.
- Waterproof seal
- Certified under the harmonized European standard EN15651 for façade, glazing, cold climate and sanitary applications in compliance with the Construction Product Regulations

Areas For Use

- Sealing glass to glass.
- Sealing glass to aluminium and metal sealing.
- Butt and Channel glazing.
- As an adhesive for fixing PVCu trims and cladding.
- Sealing around worktops and laminated panels.
- Cap glazing to metal, timber and PVCu window frames.
- For aluminium gutter sealing.
- Industrial uses, such as a gasket sealing.
- Refrigeration and hygiene seal.

Limitations

- Not for use in conjunction with bitumen or asphalt. Use WEATHER MATE
- Not for use on highly porous surfaces such as new concrete or stonework. Priming is advised or use SILICONE 450.
- Not for use on substrates that may bleed oils, solvent or plasticisers.
- Do not use in the vicinity of, or in conjunction with the edge sealant of double glazed units. Use SILICONE 450.
- Do not use for perimeter pointing of uPVC. Use SILICONE HM60 or SILICONE 450
- Do not use on soft metals such as lead or brass. Use LEADMATE SEALANT.
- Do not use for aquarium manufacture. Use AQUA MATE SEALANT.
- Non overpaintable. In applications where overpainting is required, use WEATHER MATE

Surface Preparation

All surfaces must be clean, dry and dust free. All loose or flaking surface coatings, and old sealant and mastic joints, should be removed before application. Glass, metal and aluminium should be cleaned with a proprietary solvent cleaner prior to application for optimum adhesion. Porous surfaces may require priming - a small area should be tested first.

Application

Reference should be made to the recommended joint ratios. If necessary reduce joint depth using EVERFLEX EXPANDING FILL AND FIX FOAM, or Joint backer rod. Furthermore, ensure that the joint design only permits adhesion to two surfaces, as three sided adhesion will impair flexibility.

Cut the tip of the cartridge taking care not to damage the thread. Apply nozzle and cut cleanly at an angle of 45° with an opening slightly larger than the gap to be sealed. Apply using a standard sealant gun. Best results will be obtained by keeping an even pressure on the gun trigger and keeping the gun at a constant angle to the surface being sealed.

Smooth down within 10 minutes of application. To ensure a proper bond, always smooth the sealant down using a spatula or piece of wood wetted with a soap and water solution. An improved appearance can be achieved by placing masking tape to both sides of the joint and removing within 5 minutes of application.

Specific Data

Movement accommodation	+ or -20% ISO8339 Glazing
Skinning time	5 mins @ 20°C
Cure time	4mm per 24 hours
Hardness Shore A	15-25
Shrinkage	<5%
Service temperature resistance	-40°C to + 200°C
Application temperature resistance	+5°C to + 30°C
Tensile Strength	1.2 MPa
Stress	0.3MPa at 100% elongation DIN53504
Specific gravity	~1
Cleaning	Uncured sealant white spirit; Cured sealant: EVERFLEX SILICONE EATER
Minimum joint width:	4mm
Maximum joint width	25mm
Joint ratio	Maximum depth 50% of joint width
Coverage	@ 10 linear metres 9 x 9mm fillet joint
Elongation at break	>400% ISO8339

Health & Safety

Consult MSDS for full list of hazards

Storage

Store in cool dry conditions between + 5°C and 25°C.

Shelf Life

24 months from date of manufacture

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.